

AD 6899

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
5 February 2004 (05.02.2004)

PCT

(10) International Publication Number
WO 2004/011271 A1

- (51) International Patent Classification⁷: **B41M 5/00**, (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (21) International Application Number: PCT/US2003/024116
- (22) International Filing Date: 31 July 2003 (31.07.2003)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data: 60/400,232 31 July 2002 (31.07.2002) US
- (71) Applicant (*for all designated States except US*): **E.I. DU PONT DE NEMOURS AND COMPANY** [US/US]; 1007 Market Street, Wilmington, DE 19898 (US).
- (72) Inventors; and
- (75) Inventors/Applicants (*for US only*): **SMITH, Rebecca, L.** [US/US]; 8 Merrywood Lane, Vienna, WV 26105 (US). **ELWAKIL, Hamdy** [US/US]; 10 Rivendell Court, Hockessin, DE 19707 (US).
- (74) Agent: **DOBSON, Kevin, S.**; E.I. Dupont de Nemours and Company, Legal Patent Records Center, 4417 Lancaster Pike, Wilmington, DE 19805 (US).
- Published:**
— *with international search report*
— *before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments*
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: INK-JET PRINTED RIGID INTERLAYER AND A PROCESS FOR PREPARING SAME

(57) Abstract: The present invention is a decorative glass laminate comprising a rigid interlayer bearing a printed image that has been ink-jetted onto at least one of the interlayer surfaces, and a process for preparing same. The interlayer has a storage young's modulus of 50-1000 Mla at 0.3 Hz and 25C, as determined according to ASTM D 5026-95a and a finite thickness of less than equal to about 0.38 mm.

WO 2004/011271 A1

THIS PAGE BLANK (USPTO)

INK-JET PRINTED RIGID INTERLAYER AND A PROCESS FOR PREPARING SAME

5 This Application claims the benefit of U.S. Provisional Application
No. 60/400,232, filed July 31, 2002.

BACKGROUND OF THE INVENTION

10 Laminated safety glass consists of two lites of glass joined by an
energy absorbing plastic interlayer, typically polyvinylbutyral (PVB).
Laminated safety glass is used in automotive windshields and in
architectural building glass. Architects are continually using glass in more
demanding applications such as balustrades, partitions, floors, doors, and
overhead bolted glass. Laminated safety glass using plasticized PVB as
15 the interlayer typically does not meet the strength or post glass breakage
requirements for these applications. Ionomers of ethylene/methacrylic
acid copolymers (sold under the DuPont tradename Surlyn®) yield
interlayer materials that are rigid, much stiffer and tougher than traditional
PVB interlayers. Laminated safety glass utilizing stiffer, tougher interlayer
20 has been shown to possess the strength and post glass breakage
requirements needed for these demanding architectural applications.

 In addition, it has been found that interlayers of ionomeric
ethylene/methacrylic acid copolymers demonstrate much improved edge
stability over traditional PVB interlayers. This improved edge stability
25 allows for laminated glass (with interlayers of ionomeric
ethylene/methacrylic acid copolymers) to be used in applications such as
shower doors and exterior open edge applications where traditional
laminated glass (with PVB interlayers) would not be used. In many of
these above-mentioned applications (balustrades, partitions, floors, doors,
30 overhead bolted glass, and shower doors) it would be desirable to have a
decorative image in the laminated safety glass.

Processes for making laminated decorative glass have been disclosed in WO 217154A1, DE 29706880, US 4968553, US 5914178, EP 1129844A1, and DE 20100717. These decorative laminates use PVB, PVB/PET/PVB composites, or EVA (ethylene/vinyl acetate copolymers) as the interlayer. While the resulting decorative safety glass laminates may meet the architectural safety codes, these laminates may not perform well in demanding applications such as those outlined above.

Further many of these references disclose a process for making decorative laminated glass via a silk screening process (DE 29706880, US 4968553, US 5914178, EP 1129844A1, and DE 20100717). Silk-screening an image onto an interlayer is a very time-consuming and expensive process for making decorative laminated safety glass. Ink jet technology is very flexible; any digital image can be printed onto the substrate. Using ink jet technology to print on flexible interlayers (PVB and polyurethanes) for laminated safety glass has been disclosed in WO 0218154. Several disadvantages of ink jet printing directly on PVB include the fact that all PVB interlayers have a roughened surface pattern (R_z from 30-60 μm), which is present to allow for air to escape during the lamination process as described in US 5455103. The rough surface pattern can effect image quality with respect to mottle and resolution. Also, polyvinyl butyral is a viscoelastic polymer, which can lead to poor dimensional stability in the image-bearing interlayer.

Interlayers obtained from an ionomer of an ethylene/methacrylic acid copolymer are stiff relative to other conventional interlayers, and can have improved dimensional stability relative to PVB, for example. However, the Applicants have found that one problem with printing on a stiff material is that a stiff polymer is not amenable to conventional printing processes. The Applicants have found that the process of ink jet printing on a conventional ionomeric interlayer using a conventional ink jet printer is problematical because an ionomer of ethylene/methacrylic acid copolymer is not flexible enough to be fed through the ink jet printers.

SUMMARY OF THE INVENTION

- In one aspect, the present invention is a process for ink-jet printing an image onto a rigid thermoplastic interlayer comprising the step: feeding a rigid interlayer sheet through an ink jet printer and ink-jet printing an image on the sheet, wherein the interlayer has a Storage Young's Modulus of 50-1,000 MPa (mega Pascals) at 0.3 Hz and 25°C, as determined according to ASTM D 5026-95a, and wherein the rigid interlayer sheet has a finite thickness of less than or equal to about 0.38 mm.
- In another aspect, the present invention is thermoplastic interlayer sheet bearing an image on at least one surface of the interlayer sheet, the image being printed on the sheet by a process comprising the step: feeding a rigid interlayer sheet through an ink jet printer and ink-jet printing an image on the sheet, wherein the interlayer has a Storage Young's Modulus of 50-1,000 MPa (mega Pascals) at 0.3 Hz and 25°C, as determined according to ASTM D 5026-95a, and wherein the rigid interlayer sheet has a finite thickness of less than or equal to about 0.38 mm.
- In still another aspect, the present invention is a decorative glass laminate comprising at least two sheets of glass having disposed therebetween a rigid image-bearing interlayer sheet wherein the image bearing interlayer was obtained by a process comprising the steps of: (1) "ink jet" printing pigmented ink onto at least one surface of an interlayer sheet which is a rigid ethylene/methacrylic acid copolymer ionomer having a thickness of less than or equal to about 0.38 mm and wherein the interlayer has a Storage Young's Modulus of 50-1,000 MPa (mega Pascals) at 0.3 Hz and 25°C, as determined according to ASTM D 5026-95a, to obtain an image-bearing interlayer sheet; and (2) laminating the image-bearing interlayer sheet between sheets of transparent materials to obtain a decorative laminate.

DETAILED DESCRIPTION OF THE INVENTION

In one embodiment, this invention is a method for printing a decorative image on a rigid interlayer. A rigid interlayer suitable for use in the practice of the present invention preferably has a Storage Young's Modulus of 50-1,000 MPa (mega Pascals) at 0.3 Hz and 25°C, as
5 determined according to ASTM D 5026-95a. Conventional interlayer materials, such as conventionally plasticized PVB, do not typically have a modulus in this range. Other conventional interlayer materials can be suitable as a substrate for ink-jet printing, but there are advantages in
10 using a rigid interlayer material.

Rigid, stiff Interlayers, such as those based upon ionomeric ethylene/methacrylic acid copolymers, facilitate using a much smoother surface pattern to obtain acceptable deairing during lamination since the surface pattern does not break down as rapidly with a rigid interlayer. For
15 example, a desirable range of Rz for laminating conventionally plasticized (flexible) PVB is 30-60 μm while an acceptable range of Rz for stiff interlayers is from 5 to 15 μm . The smooth surface pattern for the ionomeric interlayer yields printed images with higher resolution and less mottle than images printed directly on PVB.

20 The higher modulus of a rigid interlayer relative to other conventional flexible interlayer materials, such as flexible PVB, can yield an interlayer that has improved dimensional stability versus more flexible materials. The improved dimensional stability can improve the image stability of the image-bearing product, and make the entire process more
25 reliable and reproducible with respect to elongation or shrinkage of the image.

Printing on a rigid interlayer to obtain an image-bearing rigid with either can be accomplished using either an aqueous or solvent based ink and by using ink jet printing technology and laminating the image bearing
30 rigid interlayer between two lites of glass or other transparent materials. Laminates obtained in this manner have acceptable adhesion for safety glass applications.

In a preferred embodiment, the image is printed onto the interlayer using an inkjet printer equipped with a piezoelectric drop on demand printhead such as Spectra or Xaar and the inkjet printer is chosen so that the rigid interlayer is held on a bed type support.

5 The interlayer can be any clear, transparent rigid thermoplastic material that can be adhesively bonded to glass. The interlayer, for example, can be a PVB sheet having less than 30 parts of plasticizer, or an ionomeric interlayer. The interlayer is preferably an ionomer of an ethylene/(meth)acrylic acid copolymer where the surface roughness (R_z)
10 of the sheet is between 5 and 15 μm and the total thickness of the interlayer is between 0.38 - 2.29 mm.

The term "ethylene/(meth)acrylic acid" as used herein is a shorthand term that denotes a copolymer that comprises either ethylene and acrylic acid units or ethylene and methacrylic acid units. Ionomers are
15 known conventionally as partially neutralized ethylene/(meth)acrylic acid copolymers. A suitable interlayer for printing according to the practice of the present invention can be obtained from an ethylene/acrylic acid copolymer ionomer, such as those commercially available from E.I DuPont de Nemours and Company, for example.

20 In another embodiment, the present invention is a composite image-bearing interlayer which can be obtained by a process comprising the step of feeding a thin substrate film having Storage Young's Modulus of 50 -1,000 MPa at 0.3 Hz and 25°C, as determined according to ASTM D 5026-95a, and having a finite thickness less than or equal to about 0.38
25 mm, through a conventional ink jet printer and ink-jet printing an image onto the surface of the substrate film, and then laminating the image-bearing thin film with a second sheet of a thermoplastic interlayer material. The composite printed interlayer preferably has a thickness of from about 0.40 to about 2.29 mm. The thickness of the other sheets can vary, but
30 should be at least 0.025 mm thick. The other sheets can be blank, bear printed images or colors, can be transparent, semi-transparent, opaque or can otherwise be visually distinct from the printing substrate. In a

preferred embodiment the thin printing substrate can be laminated with a thicker (≥ 0.76 mm) film or sheet of, for example, an ionomer of an ethylene/methylacrylic acid copolymer to achieve the desired structural properties in the finished laminate. Lamination of the image-bearing interlayer sheet with a thicker polymer sheet yields a product having an image imprinted on the interlayer and also having the properties of a thicker interlayer.

The other sheet can be any thermoplastic interlayer material that can be adhesively bonded to the printed ionomer film. For example, the thicker film can be: an ethylene copolymer and/or terpolymer such as ethylene/acrylic acid or ethylene/alkyl acrylate copolymers and ethylene/acrylic acid/alkyl acrylate terpolymers; a polyacetal; a polyvinylbutyral; a polyurethane; a polyvinyl chloride; or, a polyester.

Preferably the thin printing substrate film has a thickness in the range of from about 0.025 mm to about 0.45 mm. More preferably, the thickness of the printing substrate is from about 0.1 mm to about 0.40 mm. Most preferably, the thickness of the printing substrate is from about 0.25 mm to about 0.38 mm. The thicker film sheet preferably has a thickness which is complimentary to the thickness of the thin film such that the total thickness of the interlayer sheets is in the range of from about 0.38 mm to about 2.29 mm. More preferably, the total thickness is in the range of from about 0.60 mm to about 1.75 mm. Most preferably, the total thickness of the interlayer is from about 1.14 mm to about 1.52 mm.

Laminates of the present invention can be used in any application wherein conventional (that is, non-decorative) laminated glass is used. In addition to the conventional uses as safety glass, however, the laminates of the present invention can be used as decorative articles such as picture windows, decorative countertops, graphic art, image-bearing store-front windows, displays bearing company logos, advertising media, and/or any other use wherein a transparent laminate bearing an image can be desirable.

Preferable inks for use in the practice of the present invention are those that provide printed images having a satisfactory combination of image quality, light fastness, and weatherability. Further, laminates that incorporate image-bearing interlayers of the present invention should have the adhesion properties that are acceptable in the various applications in which they will be used. Due to the nature of the polymeric interlayer substrates used herein for printing, and the requirements for adhesion in a safety glass, choice of a suitable ink is not problem free. An ink suitable for use in the practice of the present invention must also be compatible with the substrate to give satisfactory results.

Printing heads useful for piezo electric processes are available from, for example, Epson, Seiko-Epson, Spectra, XAAR and XAAR-Hitachi. Printing heads useful for thermal ink jet printing are available from, for example, Hewlett-Packard and Canon. Printing heads suitable for continuous drop printing are available from Iris and Video Jet, for example.

Optionally included in an ink system suitable for use in the practice of the present invention is a binder resin. A binder resin can be preferable to improve adhesion between the ink and the laminate substrate. Suitable binders for use in the practice of the present invention can include polyvinyl pyrrolidone/vinyl acetate (PVP/VA), polyvinyl pyrrolidone (PVP), and PUR, for example. Mixtures of binder resins can also be useful in the practice of the present invention. Other binders are conventionally known and can be useful herein.

EXAMPLES

The following examples are presented to illustrate the invention. The examples are not intended to limit the scope of the invention in any manner.

Test Methods

Surface Roughness, Rz, is determined from the 10 point average roughness as described in ISO-R468 and is expressed in microns.

Surface roughness is measured using a Mahr Federal (Providence, RI) surfanalyzer.

Dimensional Stability Test: The dimensional stability test involves printing an image of known size onto the substrate of interest. The size of
5 the printed image exit the printer is compared to that of the digital input.

Example - An image of 100 mm x 100 mm in size was printed onto a 0.38 mm thick interlayer of an ionomeric copolymer of ethylene/methacrylic acid. Immediately after printing at ambient conditions, the image was
10 determined to be exactly 100 mm x 100 mm. After the image was allowed to dry at 60°C for 30 minutes, the image size was 100 mm x 100 mm. The shrinkage for the ionomeric copolymer of ethylene/methacrylic acid was determined to be 0%.

Comparative Example - An image of 300 mm x 300 mm size was printed onto 0.76 mm PVB. Immediately after printing at ambient conditions, the image was determined to be 302 mm x 298 mm. After the image was allowed to dry at 60°C for 30 minutes, the image size was determined to be 304 mm x 294 mm. The shrinkage for 0.76 mm PVB was determined
20 to be 2%.

Lamination Procedure:

An image was printed onto the surface of each of the subject interlayers in the following examples via an ink-jet printer. Prior to lamination of the image-bearing interlayers, the interlayers were dried to less than 0.2%
25 H₂O using a 75°C oven for a minimum of 16 hours. For lamination, a layer of 15 mil blank (non-image-bearing) interlayer was placed on the image-bearing surface. The multi-layered structure was deaired (by either a vacuum bag or nip roll process) and autoclaved using standard lamination conditions.

30

Example 1. A solid yellow color block was printed onto the surface of a 0.38 mm thick interlayer of an ionomer of ethylene/methylacrylic acid

copolymer using an Epson 3000 printer. The ink used is described in the table below. The printed interlayer was laminated as described above.

Dispersion	Acrylic polymer Pigment Yellow 120 Dipropylene glycol monomethyl ether
Binder	Khrumbhaar 1717
Solvents	Dipropylene glycol methyl ether acetate
	Dipropylene glycol propyl ether

- 5 **Example 2.** A solid yellow color block was printed and laminated as described in Example 1. The ink used is described in the table below.

Dispersion	Acrylic polymer Pigment Yellow 120 Dipropylene glycol monomethyl ether
Binder	Khrumbhaar 3107
Solvents	Dipropylene glycol methyl ether acetate
	Dipropylene glycol propyl ether

Example 3. A solid yellow color block was printed and laminated as described in Example 1. The ink used is described in the table below.

Dispersion	Acrylic polymer Pigment Yellow 120 Dipropylene glycol monomethyl ether
Binder	Khrumbhaar 1728
Solvents	Dipropylene glycol methyl ether acetate
	Dipropylene glycol propyl ether

Example 4. A solid yellow color block was printed and laminated as described in Example 1. The ink used is described in the table below.

Dispersion	Acrylic polymer Pigment Yellow 120 Dipropylene glycol monomethyl ether
Binder	Laropal 80
Solvents	Dipropylene glycol methyl ether acetate
	Dipropylene glycol propyl ether

- 5 **Example 5.** A solid yellow color block was printed and laminated as described in Example 1. The ink used is described in the table below.

Dispersion	Acrylic polymer Pigment Yellow 120 Dipropylene glycol monomethyl ether
Binder	Laropal 81
Solvents	Dipropylene glycol methyl ether acetate
	Dipropylene glycol propyl ether

Example 6. A solid yellow color block was printed and laminated as described in Example 1. The ink used is described in the table below.

Dispersion	Acrylic polymer Pigment Yellow 120 Dipropylene glycol monomethyl ether
Binder	Laropal A101
Solvents	Dipropylene glycol methyl ether acetate
	Dipropylene glycol propyl ether

CLAIMS

What is claimed is:

1. A process for ink-jet printing an image onto a rigid thermoplastic interlayer comprising the step: feeding a rigid interlayer sheet through an ink jet
5 printer and ink-jet printing an image on the sheet, wherein the interlayer has a Storage Young's Modulus of 50-1,000 MPa (mega Pascals) at 0.3 Hz and 25°C, as determined according to ASTM D 5026-95a, and wherein the rigid interlayer sheet has a finite thickness of less than or equal to about 0.38 mm.
- 10 2. The process of Claim 1 wherein the interlayer is either an ethylene/(meth)acrylic acid copolymer ionomer or PVB comprising plasticizer in an amount of less than 30 parts per hundred parts based on the weight of the interlayer sheet.
3. The process of Claim 2 wherein the interlayer is an ethylene/(meth)acrylic
15 acid copolymer ionomer.
4. The process of Claim 3 further comprising the step of laminating the image-bearing interlayer sheet with a second interlayer sheet which is non-image bearing, to form a composite image-bearing interlayer, wherein the total thickness of the composite interlayer is in the range of from about
20 0.40 mm to about 2.29.
5. The process of Claim 4 wherein the image-bearing surface of the rigid interlayer is the surface that is in contact with the surface of the second interlayer sheet.
6. The process of Claim 5 wherein the second interlayer sheet is an
25 ethylene/(meth)acrylic acid copolymer ionomer.
7. The process of Claim 6 wherein the second interlayer sheet has a thickness of from about 0.76 mm to about 1.13 mm.
8. A process for obtaining a decorative laminate comprising the steps:
30 (1) "ink jet" printing pigmented ink onto at least one surface of an interlayer sheet which is a rigid ethylene/methacrylic acid copolymer ionomer having a thickness of less than or equal to about 0.38 mm and wherein the interlayer has a Storage Young's Modulus of 50-1,000 MPa (mega Pascals) at 0.3 Hz and 25°C, as determined according to ASTM D 5026-95a, to obtain an image-

bearing interlayer sheet; and (2) laminating the image-bearing interlayer sheet between sheets of transparent materials to obtain a decorative laminate.

9. The process of Claim 8 wherein the rigid interlayer comprises a
5 roughened surface having a roughness (R_z) of from about 5 μm to about 15 μm prior to lamination.
10. The process of Claim 9 wherein the rigid image-bearing interlayer is laminated with one or more other interlayer sheets to yield a composite interlayer having a total thickness of from about 0.40 mm
10 to about 2.29 mm.
11. The process of Claim 10 wherein the other interlayer comprises a thermoplastic polymer selected from polymers in the group consisting of: PVB; PET; PUR; PC; PVC; of ethylene/(meth)acrylic acid copolymer ionomers; ethylene/(meth)acrylic acid/alkyl
15 acrylates terpolymers.
12. The process of Claim 11 wherein the image is printed using a drop on demand (DOD) ink jet printing process.
13. The process of Claim 12 wherein the DOD process is a piezo electric process.
- 20 14. The process of Claim 12 wherein the DOD process is a thermal ink jet printing process.
15. The process of Claim 11 wherein the image is printed using a continuous drop ink jet printing process.
16. A decorative laminate obtained by the process of Claim 8.
- 25 17. The laminate of Claim 16 wherein the image-bearing interlayer is laminated with at least one additional sheet of at least one other interlayer to produce a composite image-bearing interlayer, wherein the at least one additional interlayer sheet has a thickness sufficient to such that the total thickness of the composite interlayer falls
30 within a range of from about 0.40 mm to about 2.29 mm, and wherein the composite image-bearing interlayer is further laminated with at least one sheet of glass.

18. The laminate of Claim 17 wherein the total thickness of the composite interlayer is in the range of from about 0.6 mm to about 1.75 mm.
- 5 19. The laminate of Claim 18 wherein the total thickness of the composite interlayer is in the range of from about 1.14 mm to about 1.52 mm.
- 10 20. A thermoplastic interlayer sheet bearing an image on at least one surface of the interlayer sheet, the image being printed on the sheet by a process comprising the step: feeding a rigid interlayer sheet through an ink jet printer and ink-jet printing an image on the sheet, wherein the interlayer has a Storage Young's Modulus of 50-1,000 MPa (mega Pascals) at 0.3 Hz and 25°C, as determined according to ASTM D 5026-95a, and wherein the rigid interlayer sheet has a finite thickness of less than or equal to about 0.38 mm.
- 15 21. The interlayer of Claim 20 wherein the interlayer has a surface roughness of from about 5 μm to about 15 μm .
22. The interlayer of Claim 21 wherein the size of the image does not change by more than $\pm 1\%$ of the initial size of the image after drying at 60°C for 30 minutes after the image is printed.

20

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 03/24116

A. CLASSIFICATION OF SUBJECT MATTER
 IPC 7 B41M5/00 B44C5/04

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 B41M B44C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 1 114 734 A (DAICEL CHEM) 11 July 2001 (2001-07-11) paragraph '0438! paragraph '0435! paragraph '0442!	1-7, 20
X	PATENT ABSTRACTS OF JAPAN vol. 2000, no. 15, 6 April 2001 (2001-04-06) & JP 2000 355163 A (KONICA CORP), 26 December 2000 (2000-12-26) abstract	1-7, 20
A	US 4 868 581 A (AKIYA TAKASHI ET AL) 19 September 1989 (1989-09-19) the whole document	1-22

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *G* document member of the same patent family

Date of the actual completion of the international search

11 December 2003

Date of mailing of the international search report

18/12/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
 NL - 2280 HV Rijswijk
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
 Fax: (+31-70) 340-3016

Authorized officer

Spyropoulou, E

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 03/24116

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 1114734	A	11-07-2001	JP 2000343811 A	12-12-2000
			JP 2001121814 A	08-05-2001
			JP 2001123075 A	08-05-2001
			JP 2001146072 A	29-05-2001
			JP 2001150804 A	05-06-2001
			JP 2001171227 A	26-06-2001
			JP 2001213046 A	07-08-2001
			JP 2001219640 A	14-08-2001
			EP 1114734 A1	11-07-2001
			WO 0074945 A1	14-12-2000
<hr/>				
JP 2000355163	A	26-12-2000	US 6432519 B1	13-08-2002
<hr/>				
US 4868581	A	19-09-1989	JP 62144986 A	29-06-1987
			JP 62153350 A	08-07-1987
<hr/>				